

DERWENT-ACC-NO: 1974-12541V

DERWENT-WEEK: 197407

COPYRIGHT 2005 DERWENT INFORMATION LTD

TITLE: Rust inhibitor - derived from dry distillation
of wood
etc

PATENT-ASSIGNEE: TOYODA H[TOYOI]

PRIORITY-DATA: 1970JP-0027309 (March 31, 1970)

PATENT-FAMILY:

PUB-NO	PUB-DATE	LANGUAGE
PAGES MAIN-IPC		
JP 74003741 B	January 28, 1974	N/A
000 N/A		

INT-CL (IPC): C23F000/00

ABSTRACTED-PUB-NO: JP 74003741B

BASIC-ABSTRACT:

The product is obtained by distilling wood from deciduous trees such as oak, beech, birch, or chestnut, and consists of an acid substance of pH 2.5-3.0, with weak oxidising properties. It may be used diluted with water, and forms a black film on the workpiece surface.

TITLE-TERMS: RUST INHIBIT DERIVATIVE DRY DISTIL WOOD

DERWENT-CLASS: G02 M14

CPI-CODES: G02-A05; G02-B03; G04-B; M14-D01; M14-K;